
CS-70-M Ceramifiable Solid Silicone Rubber with Glass Fiber Cloth in the Middle



Product Description

CS-70-M is an ultra-thin three-layer composite material with a glass fiber substrate in the middle and a uniform solid ceramic silicone rubber on both sides. It has all the characteristics of silicone rubber at room temperature. It can be transformed into a "ceramic" hard shell with self-supporting at high temperature, which has isolation effect on electricity, heat, fire and water, so as to play a good role in flame retardant, fire resistance, fire prevention and fire insulation. CS70-M is an ultra-thin material and adopts integrated molding technology and integrates the advantages of ceramized silicone rubber and glass fiber cloth. It is an ideal choice for fire insulation and flame retardant materials in railway transportation, industrial environments and electronic equipment.

Features and Advantages

- Long term withstand 1000 ℃ flame temperature without burning
- Ceramic support can be formed above 600℃
- Compliance with smoke, fire and toxicity requirements
- Excellent fire resistance
- Good resistance to aging and chemical stability

Typical Application

- Power battery pack cover with fire insulation material
- Battery module fire insulation filler
- Other fire-proof seal applications

Product Specification

- Substrate: Glass fiber cloth substrate
- Roll form: Product size can be customized according to customer requirements
- Shape: Can be die cut into various shapes
- Adhesive: No adhesive, single-sided or double-sided adhesive

Storage and Transportation

- Store in original packaging at room temperature
- Keep out open flames
- Handling and transportation as general chemicals
- Non-toxic and non-dangerous

Shelf-life

- Without Adhesive: 10 years
- With Adhesive: According to the type of adhesive

The true and reliable data information contained in this information is intended to assist you in the design of the use of the TAIYA solid silicone rubber, based on the scope of application of the product determined by our current cognition and experience, unintentionally and does not constitute any warranty, express or implied, including any warranties of merchantability to the commodity, fitness for special purposes, and does not guarantee that the user can achieve the results shown in this data for a particular purpose. For applications outside the scope, or for use under different conditions and environments, the resulting results will not be liable. Therefore, we strongly recommend that the user determine the suitability of the product before use.

Release date: 2024-11-01

Dongguan Taiyaluck Electronic Technology Co., Ltd. TEL: 0769-89793287 htttp://www.taiya.cn
Address: 36 Yongfu Street, Miaobian, Liaobu Town, Dongguan, Guangdong Province, China

CS-70-M Ceramifiable Solid Silicone Rubber with Glass Fiber Cloth in the Middle

TAIYALUCK

Product Physical Properties

Properties	Test Method	Typical Value
Product	/	CS-70-M
Color	Visual	Gray, Black
Thickness (mm) Tolerance (%)	ASTM D374/D374M /	0.2~0.5 ±15
Density (g/cm^3) (Pure silicone rubber)	ASTM D792	1.6
Hardness (Shore A)	ASTM D2240	>65
*Tensile Strength (MPa, min)	ASTM D412	20
*Tear Strength (N/mm, min)	ASTM D624	25
Thermal Conductivity (W/(m·K))	ASTM E1461	0.3
Dielectric Strength (kV/mm)	ASTM D149	>20
Volume Resistivity (Ω•cm)	ASTM D257	>10^{10}
Burning Test (1200℃，30 min)	Internal	No crack
Recommended Temperature (℃)	SAE J-2236	-60~220

*Cut the sample according to the glass fiber weaving direction determined internally.

Note: The above data is the average of the overall test, and we can be contacted for more product information.

The true and reliable data information contained in this information is intended to assist you in the design of the use of the TAIYA solid silicone rubber, based on the scope of application of the product determined by our current cognition and experience, unintentionally and does not constitute any warranty, express or implied, including any warranties of merchantability to the commodity, fitness for special purposes, and does not guarantee that the user can achieve the results shown in this data for a particular purpose. For applications outside the scope, or for use under different conditions and environments, the resulting results will not be liable. Therefore, we strongly recommend that the user determine the suitability of the product before use.

Release date: 2024-11-01

Dongguan Taiyaluck Electronic Technology Co., Ltd. TEL: 0769-89793287 htttp://www.taiya.cn
Address: 36 Yongfu Street, Miaobian, Liaobu Town, Dongguan, Guangdong Province, China